

PURUS® ALLETOR® HEAVY DUTY HI-TEMP GREASE WITH 3% MOLY

DESCRIPTION: PURUS® Alleto[®] Heavy Duty Hi-Temp Grease with 3% Moly is a premium quality lithium complex grease treated with 3% molybdenum disulfide for additional protection against wear. It is available in NLGI #1 and NLGI #2 grades. It has excellent water spray-off and washout resistance, gives excellent performance in the areas of oxidation stability and corrosion protection and resists leakage, dripping or undesirable throw-off from the lubricated surface.

PURUS® Alleto[®] Heavy Duty Hi-Temp Grease with 3% Moly applications include wheel bearings and universal joints, off-highway and construction equipment, trucking, mining and farming equipment as well as many other industrial applications.

**PERFORMANCE
BENEFITS:**

- Contains 3 percent molybdenum for added wear protection
- Premium quality lithium complex, Extreme Pressure (EP) grease
- Outstanding protection in wet environments
- Excellent fifth wheel grease
- Superior protection to lubricate a wide variety of severe duty applications both on and off-road

**TYPICAL
PROPERTIES*:**

	NLGI No. 1	NLGI No. 2
Thickener	Lithium Complex	Lithium Complex
Texture	Smooth, Tacky	Smooth, Tacky
Color, Observed	Gray/Black	Gray/Black
Worked 60 Penetration, D 217	310-330	265-295
Dropping Point, ASTM D 566, °F	500	>500
Water Washout, ASTM D 1264, % loss @ 175°F	3	1
Rust Prevention, ASTM D 1743	Pass	Pass
Copper Corrosion, ASTM D 4048	1B	1B
Timken EP Test, OK Load, ASTM D 2509, lb	60	60
Four-Ball Wear, ASTM D 2266, mm	0.57	0.57
Four-Ball EP Weld Point, ASTM D 2596, kgf	400	400
Four-Ball Load Wear Index, ASTM D 2596, kgf	49.8	49.8
U.S. Steel Mobility, LT-37, g/min		
77F	732	690
32F	55	50
Lincoln Ventmeter, K95400, Psi		
77F	105	200
32F	147	344
0F	433	1,224
Base Oil Viscosity, ASTM D 445		
at 40°C, cSt	220	220
at 100°C, cSt	20	20
Viscosity Index, ASTM D 2270	105	105
Operating Temperature Range, °F (°C)	-20 to 325 (-28 to 163)	-10 to 325 (-23 to 163)
NLGI Certified, ASTM D 4950	GC-LB	GC-LB

*Due to continual product research and development, the information contained herein is based on products purchased in the U.S. and subject to change without notification. Typical properties may vary slightly.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Safety Data Sheets are available for all of our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either AIOD or its affiliates for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult your local AIOD Distributor if you require any further information.



Revised: 11/2017
PINHDHTG